



دهانات جدة
Jeddah Paints
Since 1983

JP Graffiato Fine-Tegrafo 10-200

Product Data Sheet

Product Description: JP Graffiato Fine is an exterior emulsified acrylic texture paint with extended durability, aesthetic enhancement, protective properties against UV radiation and moisture, and their ability to hide imperfections, crack resistant and is suitable for hot climate.

Area of Use: It is recommended as a decorative finish coat, exterior or interior, on block walls, precast concrete features and panels, gypsum and fibre cement walls and features, concrete plastered surfaces, bricks, and stucco to create fine texture pattern, a wall finish for protection and decoration.

PHYSICAL CONSTANTS	
Colour	White, other color limited and tinted
Appearance	Textured
Solid Volume	80%
Theoretical Coverage	2 Kg/Square meter
Density	1.8 Kg/L
Touch dry	2-3 hours
Full Cure	24 hours
VOC	5 g/l

APPLICATION DETAILS	
Application method	Trowel
Thinner	None, Clean tool with fresh water
Thinner %	Do not thin
Airless nozzle orifice	N.A.
Airless nozzle pressure	N.A.
Recommended DFT	1mm
Corresponding WFT	1.2 mm
Use life	12 hours

Note: The texture shall be thoroughly mixed prior to application. Practical spreading rate/consumption will vary and is influenced by the porosity and nature of the substrate, micro-environment, application method and workmanship.

Application Conditions: Application temperature above 5°C and humidity below 85%. Adequate ventilation to be provided during application and drying. Do not apply in severe weather conditions.

Surface Preparation:

The concrete should be fully cured. The substrate should be dry, clean, free from dust or dirt and any other contamination. For absorbent surfaces, first stabilize them using JP concrete primer.

Application Procedure:

Mix using a low speed mixer. Apply manually or by using spray machine direct in one coat of a thickness of 1mm to 1.5 mm. level with a metal trowel to achieve a uniform, continuous layer. When the layer is not yet dry (after about 5 minutes to 10 minutes) finish by smoothing with a plastic trowel, moving the tool vertically, horizontally or in circles, depending on the desired effect.

Preceding Coats : JP primer and JP Putty, as per the specification.

Subsequent Coats: JP emulsion if required to change color

Storage: Follow local legislation for storage. Avoid storage in direct sunlight preferably covered area with maximum temperature of 40°C and not below 5°C, protect from rain.

Shelf Life: 2 years when stored in shaded spaces.

Safety : Observe all safety labels on packaging and paint containers during application. Follow Material Safety Data Sheets and all local or national safety regulations. Application should be done only in well ventilated areas. Take precautions with contact with skin, eyes, inhalation. Take precautions against possible risks of fire or explosions and protect the environment. For professional use only.